


Overview

KEMET's Automotive Grade Series surface mount capacitors in X7R dielectric are suited for a variety of applications requiring proven, reliable performance in harsh environments. Whether under-hood or in-cabin, these devices emphasize the vital and robust nature of capacitors required for mission and safety critical automotive circuits. Stricter testing protocol and inspection criteria have been established for automotive grade products in recognition of potentially harsh environmental conditions . KEMET automotive grade series capacitors meet the demanding Automotive Electronics Council's AEC–Q200 qualification requirements

X7R dielectric features a 125°C maximum operating temperature and is considered "temperature stable," The Electronics Industries Alliance (EIA) characterizes X7R dielectric as a Class II material. Components of this classification are fixed, ceramic dielectric capacitors suited for bypass and decoupling applications or for frequency discriminating circuits where Q and stability of capacitance characteristics are not critical. X7R exhibits a predictable change in capacitance with respect to time and voltage and boasts a minimal change in capacitance with reference to ambient temperature. Capacitance change is limited to $\pm 15\%$ from -55° C to $+125^{\circ}$ C.

Benefits

- · AEC-Q200 automotive qualified
- -55°C to +125°C operating temperature range
- · Lead (Pb)-Free, RoHS and REACH compliant
- Temperature stable dielectric
- EIA 0402, 0603, 0805, 1206, 1210, 1812, and 2220, case sizes
- DC voltage ratings of 6.3 V, 10 V, 16 V, 25 V, 50 V, 100 V, 200 V, and 250 V
- Capacitance offerings ranging from 10 pF to 22 μF
- Available capacitance tolerances of ±5%, ±10%, and ±20%
- · Non-polar device, minimizing installation concerns
- 100% pure matte tin-plated termination finish allowing for excellent solderability



Ordering Information

С	0805	С	225	М	4	R	Α	С	AUTO
Ceramic	Case Size (L" x W")	Specification/ Series	Capacitance Code (pF)	Capacitance Tolerance	Rated Voltage (VDC)	Dielectric	Failure Rate/ Design	Termination Finish ¹	Packaging/Grade (C-Spec)
	0402 0603 0805 1206 1210 1812 2220	C = Standard	Two significant digits + number of zeros.	J = ±5% K = ±10% M = ±20%	9 = 6.3 8 = 10 4 = 16 3 = 25 5 = 50 1 = 100 2 = 200 A = 250	R = X7R	A = N/A	C = 100% Matte Sn	See "Packaging C-Spec Ordering Options Table" below

¹ Additional termination finish options may be available. Contact KEMET for details



Packaging C-Spec Ordering Options Table

Packaging Type ¹	Packaging/Grade Ordering Code (C-Spec) ³
7" Reel	AUTO
13" Reel / Unmarked	AUTO7411 (EIA 0603 and smaller case sizes) AUTO7210 (EIA 0805 and larger case sizes)
7" Reel/Unmarked/2 mm pitch ²	3190
13" Reel/Unmarked/2 mm pitch ²	3191

¹ Reeling tape options (Paper or Plastic) are dependent on capacitor case size (L" x W") and thickness dimension. See "Chip Thickness/Tape & Reel Packaging Quantities" and "Tape & Reel Packaging Information".

² The 2 mm pitch option allows for double the packaging quantity of capacitors on a given reel size. This option is limited to EIA 0603 (1608 metric) case size devices. For more information regarding 2 mm pitch option see "Tape & Reel Packaging Information".

³ All Automotive packaging C-Specs listed exclude the option to laser mark components. Please contact KEMET if you require a laser marked option. For more information see "Capacitor Marking".

³ For additional Information regarding "AUTO" C-Spec options, see "Automotive C-Spec Information".

Benefits cont'd

- Capacitance offerings ranging from 10 pF to 22 µF
- Available capacitance tolerances of ±5%, ±10%, and ±20%
- · Non-polar device, minimizing installation concerns
- 100% pure matte tin-plated termination finish allowing for excellent solderability

Applications

Typical applications include decoupling, bypass, filtering and transient voltage suppression.

Qualification/Certification

Automotive Grade products meet or exceed the requirements outlined by the Automotive Electronics Council. Details regarding test methods and conditions are referenced in document AEC–Q200, Stress Test Qualification for Passive Components. For additional information regarding the Automotive Electronics Council and AEC–Q200, please visit their website at www.aecouncil.com.

Environmental Compliance

Lead (Pb)-Free, RoHS, and REACH compliant without exemptions.



Automotive C-Spec Information

KEMET Automotive Grade products meet or exceed the requirements outlined by the Automotive Electronics Council. Details regarding test methods and conditions are referenced in document AEC–Q200, Stress Test Qualification for Passive Components. These products are supported by a Product Change Notification (PCN) and Production Part Approval Process warrant (PPAP).

Automotive products offered through our distribution channel have been assigned an inclusive ordering code C-Spec, "AUTO". This C-Spec was developed in order to better serve small and medium sized companies that prefer an automotive grade component without the requirement to submit a customer Source Controlled Drawing (SCD) or specification for review by a KEMET engineering specialist. This C-Spec is therefore not intended for use by KEMET's OEM Automotive customers and are not granted the same "privileges" as other automotive C-Specs. Customer PCN approval and PPAP request levels are limited (see details below).

Product Change Notification (PCN)

The KEMET Product Change Notification system is used to communicate primarily the following types of changes:

- · Product/process changes that affect product form, fit , function, and /or reliability
- · Changes in manufacturing site
- Product obsolescence

KEMET Automotive	Customer Noti	fication due to:	Days prior to
C-Spec	Process/Product change	Obsolescence*	implementation
KEMET assigned ¹	Yes (with approval and sign off)	Yes	180 days Minimum
AUTO	Yes (without approval)	Yes	90 days Minimum

¹ KEMET assigned C-Specs require the submittal of a customer SCD or customer specification for review. For additional information contact KEMET.

Production Part Approval Process (PPAP)

The purpose of the Production Part Approval Process is:

- To ensure that supplier can meet the manufacturability and quality requirements for the purchased parts.
- To provide the evidence that all customer engineering design record and specification requirements are properly understood and fulfilled by the manufacturing organization.
- To demonstrate that the established manufacturing process has the potential to produce the part

KEMET Automotive		PPAP (Product	Part Approval	Process) Level	
C-Spec	1	2	3	4	5
KEMET assigned ¹	•	•	•	•	•
AUTO	0		0		


¹ KEMET assigned C-Specs require the submittal of a customer SCD or customer specification for review. For additional information contact KEMET.

• Part Number specific PPAP available

• Product family PPAP only



Dimensions – Millimeters (Inches)



EIA Size Code	Metric Size Code	L Length	W Width	T Thickness	B Bandwidth	S Separation Minimum	Mounting Technique
0402	1005	1.00 (.040) ± 0.05 (.002)	0.50 (.020) ± 0.05 (.002)		0.30 (.012) ± 0.10 (.004)	0.30 (.012)	Solder Reflow Only
0603	1608	1.60 (.063) ± 0.15 (.006)	0.80 (.032) ± 0.15 (.006)		0.35 (.014) ± 0.15 (.006)	0.70 (.028)	
0805	2012	2.00 (.079) ± 0.20 (.008)	1.25 (.049) ± 0.20 (.008)		0.50 (0.02) ± 0.25 (.010)	0.75 (.030)	Solder Wave or Solder Reflow
1206	3216	3.20 (.126) ± 0.20 (.008)	1.60 (.063) ± 0.20 (.008)	See Table 2 for Thickness	0.50 (0.02) ± 0.25 (.010)		
1210 ¹	3225	3.20 (.126) ± 0.20 (.008)	2.50 (.098) ± 0.20 (.008)		0.50 (0.02) ± 0.25 (.010)	N1/A	
1812	4532	4.50 (.177) ± 0.30 (.012)	3.20 (.126) ± 0.30 (.012)		0.60 (.024) ± 0.35 (.014)	N/A	Solder Reflow Only
2220	5650	5.70 (.224) ± 0.40 (.016)	5.00 (.197) ± 0.40 (.016)		0.60 (.024) ± 0.35 (.014)		

¹ For capacitance values \geq 4.7 μ F add 0.02 (0.001) to the width tolerance dimension and 0.10 (0.004) to the length tolerance dimension.

Electrical Parameters/Characteristics

Item	Parameters/Characteristics
Operating Temperature Range	−55°C to +125°C
Capacitance Change with Reference to +25°C and 0 Vdc Applied (TCC)	±15%
¹ Aging Rate (Maximum % Capacitance Loss/Decade Hour)	3.0%
² Dielectric Withstanding Voltage (DWV)	250% of rated voltage (5 ± 1 seconds and charge/discharge not exceeding 50mA)
³ Dissipation Factor (DF) Maximum Limit @ 25°C	5%(6.3V & 10V), 3.5%(16V & 25V) and 2.5%(50V to 250V)
⁴ Insulation Resistance (IR) Minimum Limit @ 25°C	See Insulation Resistance Limit Table (Rated voltage applied for 120 ± 5 secs @ 25°C)

¹Regarding Aging Rate: Capacitance measurements (including tolerance) are indexed to a referee time of 1,000 hours.

²DWV is the voltage a capacitor can withstand (survive) for a short period of time. It exceeds the nominal and continuous working voltage of the capacitor. ³Capacitance and dissipation factor (DF) measured under the following conditions:

1kHz ± 50Hz and 1.0 ± 0.2 Vrms if capacitance ≤10 μ F

120Hz \pm 10Hz and 0.5 \pm 0.1 Vrms if capacitance >10 μ F

⁴To obtain IR limit, divide $M\Omega$ - μ F value by the capacitance and compare to G Ω limit. Select the lower of the two limits.

Note: When measuring capacitance it is important to ensure the set voltage level is held constant. The HP4284 & Agilent E4980 have a feature known as Automatic Level Control (ALC). The ALC feature should be switched to "ON".

5

Post Environmental Limits

	High Tempo	erature Life, E	Biased Humid	lity, Moisture	Resistance	
Dielectric	Case Size	Rated DC Voltage	Capacitance Value	Dissipation Factor (Maximum %)	Capacitance Shift	Insulation Resistance
		< 16		7.5		
	0402	16/25	All	5.0		
		> 25		3.0		
		< 16		7.5		
	0603	16/25	All	5.0		
		> 25		3.0		
		< 16		7.5		
	0805	16/25	All	5.0		
		0805 16/25 > 25 < 16		3.0		
		< 16	All	7.5		
X7R		16	< 10 µF	5.0	± 20%	10% of Initial
	1206	10	≥ 10 µF	20.0	± 20%	Limit
		25	All	5.0		
		> 25	All	3.0		
		< 16	All	7.5		
		16	All	5.0		
	1210	25	< 10 µF	5.0		
			≥ 10 µF	20.0		
		> 25	All	3.0		
	1808	< 16		7.5		
	1812 2220	16/25	All	5.0		
	2225	> 25		3.0		



Dissipation Factor (DF) Limits Table

EIA Case Size	Rated DC Voltage	Capacitance	Dissipation Factor (Maximum %)				
	< 16		5.0				
0402	16/25	All	3.5				
	> 25		2.5				
	< 16		5.0				
0603	16/25	All	3.5				
	> 25		2.5				
	< 16		5.0				
0805	16/25	All	3.5				
	> 25		2.5				
	< 16	All	5.0				
	16	< 10 µF	3.5				
1206		≥ 10 µF	10.0				
	25	All	3.5				
	> 25	All	2.5				
	< 16	All	5.0				
	16	All	3.5				
1210	05	< 10 µF	3.5				
	25	≥ 10 µF	10.0				
	> 25	All	2.5				
1808	< 16		5.0				
1812 2220	16/25	All	3.5				
2225	> 25		2.5				

Insulation Resistance Limit Table

EIA Case Size	1,000 Megohm Microfarads or 100 GΩ	500 Megohm Microfarads or 10 GΩ
0201	N/A	ALL
0402	< 0.012 µF	≥ 0.012 µF
0603	< 0.047 µF	≥ 0.047 µF
0805	< 0.15 µF	≥ 0.15 µF
1206	< 0.47 µF	≥ 0.47 µF
1210	< 0.39 µF	≥ 0.39 µF
1808	ALL	N/A
1812	< 2.2 µF	≥ 2.2 µF
1825	ALL	N/A
2220	< 10 µF	≥ 10 µF
2225	ALL	N/A



Table 1A – Capacitance Range/Selection Waterfall (0402 – 1206 Case Sizes)

3,900 pF 4,700 pF 5,600 pF	392 472 562	J J J	K K K	M M M	BB BB BB	BB BB BB	BB BB BB	BB BB BB	BB BB BB	CF CF CF	CF CF CF	CF CF CF	CF CF CF	CF CF CF	CF CF CF	CF CF CF	DN DN DN	DN DN DN	DN DN DN	DN DN DN	DN DN DN	DN DN DN	DN DN DN	DN DN DN	EB	EB EB EB	EB EB EB	EB EB EB	EB EB EB	EB EB EB	EB EB EB	EB EB EB
6,800 pF 8,200 pF 10,000 pF	682 822 103	JJ	K K K	M M M	BB BB BB	BB BB BB	BB BB BB	BB BB BB	BB BB BB	CF CF CF	CF CF CF	CF CF CF	CF CF CF	CF CF CF	CF CF CF	CF CF CF	DN DN DN	DN DN DN	DN DN DN	DN DN DN	DN DN DN	DN DN DN	DN DN DN	DN DN DN	EB EB	EB EB EB	EB EB EB	EB EB EB	EB EB EB	EB EB EB	EB EB EB	EB EB EB
12,000 pF 15,000 pF 18,000 pF	123 153 183	J J J	K K K	M	BB BB BB	BB BB BB	BB BB BB	BB BB BB	BB BB BB	CF CF CF	CF CF CF	CF CF CF	CF CF CF	CF CF CF	CF CF CF	0	DN DN DN	DN DN DN	DN DN DN	DN DN DN	DN DN DN	DN DP DP	DN DN DN	DN DN DN	EB EB	EB EB EB	EB EB EB	EB EB EB	EB EB EB	EB EB	EB	EB EB EB
22,000 pF 27,000 pF 33,000 pF	223 273 333	JJ	K K K	M	BB BB BB	BB BB BB	BB BB BB	BB BB BB	BB	CF CF CF	CF CF CF	CF CF CF	CF CF CF	CF CF CF	CF CF CF		DN DN DN	DN DN DN	DN DN DN	DN DN DN	DN DN DN	DP DP DP		DN		EB EB EB	EB EB EB	EB EB EB	EB EB EB	EB EB		EB EB EB
39,000 pF 47,000 pF 56,000 pF	393 473 563	J J J	K K K	M M M	BB BB BB	BB BB BB	BB BB BB	BB BB		CF CF CF	CF CF CF	CF CF CF	CF CF CF	CF CF CF	CF CF		DN DN DP	DN DN DP	DN DN DP	DN DN DP	DN DN DP	DP DE DE	DE DG DG		EB EB	EB EB EB	EB EB EB	EB EB EB	EB EB EB	EC EC EB	EB ED	ED ED ED
68,000 pF 82,000 pF 0.10 μF	683 823 104	J J	K K K	M M M	BB BB BB	BB BB BB	BB BB BB			CF CF CF	CF CF CF	CF CF CF	CF CF CF	CF CF CF			DP DP DN	DP DP DN	DP DP DN	DP DP DN	DP DP DN	DE DE DE			EB EB EB	EB EB EB	EB EB EB	EB EB EB	EB EB EB	EB EB EB		ED ED EM
0.12 μF 0.15 μF 0.18 μF	124 154 184 224	J J J	K K K	M M M						CF CF CF CF	CF CF CF CF	CF CF CF CF	CF CF CF CF	CF CF			DN DN DN DN	DN DN DN	DN DN DN DN	DN DN DN DN	DP DP DP DP	DG DG DG DG			EC EC EC EC	EC EC EC EC	EC EC EC EC	EC EC EC EC	EC EC EC	EC EC EC	EG EG	
0.22 μF 0.27 μF 0.33 μF 0.39 μF	224 274 334 394)))	K K K	M M M						CF CF CF CF	CF CF CF CF	CF CF CF CF	CF				DR DP DP DG	DN DP DP DG	DN DP DP DG	DN DP DP DG	DP DP DP DE	DG			EC EB EB EB	EC EB EB EB	EC EB EB EB	EC EB EB EB	EC EC EC EC	EC EM EG EG		
0.47 μF 0.56 μF 0.68 μF	474 564 684	J J J	K K K	M M M						CF	CF	CF					DP DP DP	DP DP DP	DP DP DP	DP DG DG	DE DH DH				EC ED EE	EC ED EE	EC ED EE	EC ED EE	EC EC ED	EG		
0.82 μF 1.0 μF 1.2 μF	824 105 125	J J J	K K K	M M M													DP DP	DP	DP DP	DG					EF EF ED	EF EF ED	EF EF	EF EG	ED ED			
1.5 μF 1.8 μF 2.2 μF	155 185 225	J J J	K K K	M M M													DG DG	DG DG DG	DG DG						EF ED ED	EF ED ED	EF ED ED	EG EF	EH EH			
2.7 μF 3.3 μF 3.9 μF	275 335 395	J J J	K K K	M M M																					EN ED EF		EN ED	EH				
			ed Voli (VDC)	tage	6.3	6	16	25	50	6.3	10	16	25	50	100	200	6.3	6	16	25	50	100	200	250	6.3	9	16	25	50	100	200	250
	Cap								_							_			-							-					\rightarrow	

*Capacitance range includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82 and 91) **Capacitance range includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68 and 82)



Table 1A – Capacitance Range/Selection Waterfall (0402 – 1206 Case Sizes) cont'd

			se (Seri	Size es		C)40	2 C				C)60:	3C					(208	050	;					(C12	060	;		
Capacitance	Сар	Vo	tage	Code	9	8	4	3	5	9	8	4	3	5	1	2	9	8	4	3	5	1	2	A	9	8	4	3	5	1	2	Α
Capacitance	Code	Rat	ed Vo (VDC	oltage C)	6.3	9	16	25	50	6.3	10	16	25	50	100	200	6.3	10	16	25	50	100	200	250	6.3	10	16	25	50	100	200	250
			pacit olera			Pro	duc	t Av	/aila	abili	ty a	nd	Chip	o Th	ickı	nes	s Co	des	s – S	See	Tab	le 2	for	Ch	ір Т	hick	nes	s D	ime	nsi	ons	
4.7 µF	475	J	K	M																					EF	EF	EF	EH				
5.6 µF	565	J	K	M																					EH	EH	EH					
6.8 µF	685	J	K	M																					EH	EH	EH					
8.2 µF	825	J	K	M																					EH	EH	EH					
10 µF	106	J	K	M																					EH	EH	EH					
		Rat	ed Vo (VDC	oltage C)	6.3	10	16	25	50	6.3	10	16	25	50	100	200	6.3	10	16	25	50	100	200	250	6.3	10	16	25	50	100	200	250
Capacitance	Cap Code	Vo	tage	Code	9	8	4	3	5	9	8	4	3	5	1	2	9	8	4	3	5	1	2	A	9	8	4	3	5	1	2	Α
	2000		ise (Seri	Size es		C	0402	2C				C	0603	BC						C08	05C	;						C12	06C	:		

*Capacitance range includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82 and 91) **Capacitance range includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68 and 82)

Table 1B – Capacitance Range/Selection Waterfall (1210 – 2220 Case Sizes)

			se S Serie	Size es				C12	100	;			C	1808	BC		C	1812	2C			C18	250	;		C	2220)C	
Capacitance	Сар	Volt	age C	Code	9	8	4	3	5	1	2	A	5	1	2	3	5	1	2	Α	5	1	2	A	3	5	1	2	A
Capacitance	Code		ed Vol (VDC		6.3	10	16	25	50	100	200	250	50	100	200	25	50	100	200	250	50	100	200	250	25	50	100	200	250
			oacita oleran		F	Prod	uct	Ava	ilabi	lity	and	Chi	o Th	ickn	ess	Cod	les -	- Se	e Ta	ble 2	2 for	[.] Chi	p Tł	nickı	ness	Din	nens	ion	s
10 - 91 pF*	100 - 910*	J	K	М	FB	FB	FB	FB	FB	FB	FB																		
100 - 270 pF**	101 - 391**	J	K	M	FB	FB	FB	FB	FB	FB	FB																		
330 pF	331	J	K	M	FB	FB	FB	FB	FB	FB	FB		LF	LF	LF														
390 pF	391	J	K	M	FB	FB	FB	FB	FB	FB	FB		LF	LF	LF														
470 - 820 pF**	471 - 821**	J	K	Μ	FB	FB	FB	FB	FB	FB	FB		LF	LF	LF	GB	GB	GB	GB										
1,000 pF	102	J	K	M	FB	FB	FB	FB	FB	FB	FB		LF	LF	LF	GB	GB	GB	GB										
1,200 pF	122	J	K	M	FB	FB	FB	FB	FB	FB	FB		LF	LF	LF	GB	GB	GB	GB										
1,500 pF	152	J	K	M	FB	FB	FB	FB	FB	FB	FE		LF	LF	LF	GB	GB	GB	GB										
1,800 pF	182	J	K	M	FB	FB	FB	FB	FB	FB	FE		LF	LF	LF	GB	GB	GB	GB										
2,200 pF	222	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LF	LF	LF	GB	GB	GB	GB										
2,700 pF	272	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LF	LF	LF	GB	GB	GB	GB										
3,300 pF	332	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LF	LF		GB	GB	GB	GB										
3,900 pF	392	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LF	LF		GB	GB	GB	GB		I I								
4,700 pF	472	J	К	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GD		1								
5,600 pF	562	J	К	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GH		1								
6,800 pF	682	J	K	М	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GB	GB					JE	JE	JE		
8,200 pF	822	J	к	М	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GB	GB					JE	JE	JE		
10,000 pF	103	J	к	М	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GB	GB					JE	JE	JE		
12,000 pF	123	J	к	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GB	GB	i i				JE	JE	JE		
			ed Vol (VDC		6.3	9	16	25	50	100	200	250	50	100	200	25	50	100	200	250	50	100	200	250	25	50	100	200	250
Capacitance	Cap Code	Volt	age C	Code	9	8	4	3	5	1	2	A	5	1	2	3	5	1	2	Α	5	1	2	Α	3	5	1	2	A
			se S Serie					C12	10C				С	1808	SC		С	1812	C			C18	25C			C	2220	C	

*Capacitance range includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82 and 91) **Capacitance range includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68 and 82)



Table 1B – Capacitance Range/Selection Waterfall (1210 – 2220 Case Sizes) cont'd

			se S Serie			1		C12	10C	•	ſ		C	1808	BC		C	1812	2C	1		C18	250	;		C	222()C	ſ
Capacitance	Сар	Volt	tage C	Code	9	8	4	3	5	1	2	A	5	1	2	3	5	1	2	A	5	1	2	A	3	5	1	2	Α
	Code		ed Vol (VDC)		6.3	10	16	25	50	100	200	250	50	100	200	25	50	100	200	250	50	100	200	250	25	50	9	200	250
			pacita pleran		6	Prod	luct	Ava	ilabi	lity	and	Chi	p Th	ickn	ess	Coc	les -	- Se	e Ta	ble 2	2 for	Chi	p Tł	nickı	ness	s Dir	nens	sion	s
15,000 pF	153	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GB	GB					JE	JE	JE		
18,000 pF	183	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GB	GB					JE	JE	JE		
22,000 pF	223	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GB	GB	HB	HB	HB	HB	JE	JE	JE		
27,000 pF	273	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GB	GB	HB	HB	HB	HB	JE	JE	JE		
33,000 pF	333	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GB	GB	HB	HB	HB	HB	JB	JB	JB		
39,000 pF	393	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GB	GB	HB	HB	HB	HB	JB	JB	JB		
47,000 pF	473	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GB	GB	HB	HB	HB	HB	JB	JB	JB		
56,000 pF	563	J	K	M	FB	FB	FB	FB	FB	FB	FC	FC	LD	LD		GB	GB	GB	GB	GB	HB	HB	HB	HB	JB	JB	JB		
68,000 pF	683	J	K	M	FB	FB	FB	FB	FB	FB	FC	FC	LD			GB	GB	GB	GB	GB	HB	HB	HB	HB	JB	JB	JB		
82,000 pF	823	J	K	M	FB	FB	FB	FB	FB	FC	FF	FF	LD			GB	GB	GB	GB	GB	HB	HB	HB	HB	JB	JB	JC	JC	JC
0.10 µF	104	J	K	M	FB	FB	FB	FB	FB	FD	FG	FG	LD			GB	GB	GB	GB	GB	HB	HB	HB	HB	JB	JB	JC	JC	JC
0.12 µF	124	J	K	M	FB	FB	FB	FB	FB	FD	FH	FH	LD			GB	GB	GB	GB	GB	HB	HB	HB	HB	JB	JB	JC	JC	JC
0.15 µF	154	J	K	M	FC	FC	FC	FC	FC	FD	FM	FM	LD			GB	GB	GB	GE	GE	HB	HB	HB	HB	JB	JB	JC	JC	JC
0.18 µF	184	J	K	M	FC	FC	FC	FC	FC	FD	FK	FK	LD			GB	GB	GB	GG	GG	HB	HB	HB	HB	JB	JB	JC	JC	JC
0.22 µF	224	J	K	M	FC	FC	FC	FC	FC	FD	FK	FK				GB	GB	GB	GG	GG	HB	HB	HB	HB	JB	JB	JC	JC	JC
0.27 µF	274	J	K	M	FC	FC	FC	FC	FC	FD						GB	GB	GG	GG	GG	HB	HB	HB	HB	JC	JC	JC	JC	JC
0.33 µF	334	J	K	M	FD	FD	FD	FD	FD	FD						GB	GB	GG	GG	GG	HB	HB	HB	HB	JC	JC	JC	JC	JC
0.39 µF	394	J	K	M	FD	FD	FD	FD	FD	FD						GB	GB	GG	GG	GG	HD	HD	HD	HD	JC	JC	JC	JC	JC
0.47 µF	474	J	K	M	FD	FD	FD	FD	FD	FD						GB	GB	GG	GJ	GJ	HD	HD	HD	HD	JC	JC	JC	JC	JC
0.56 µF	564	J	K	M	FD	FD	FD	FD	FD	FF						GC	GC	GG			HD	HD	HD	HD	JC	JD	JD	JD	JD
0.68 µF	684	J	K	M	FD	FD	FD	FD	FD	FG						GC	GC	GG			HD	HD	HD	HD	JC	JD	JD	JD	JD
0.82 µF	824	J	K	M	FF	FF	FF	FF	FF	FL						GE	GE	GG			HF	HF	HF	HF	JC	JF	JF	JF	JF
1.0 µF	105	J	K	M	FH	FH	FH	FH	FH	FM						GE	GE	GG			HF	HF	HF	HF	JC	JF	JF	JF	JF
1.2 µF	125	J	K	M	FH	FH	FH	FH	FG																JC	JC			
1.5 µF	155	J	K	M	FH	FH	FH	FH	FG																JC	JC			
1.8 µF	185	J	K	M	FH	FH	FH	FH	FG																JD	JD			
2.2 µF	225	J	K	M	FJ	FJ	FJ	FJ	FG							GO	GO								JF	JF			
2.7 µF	275	J	K	M	FE	FE	FE	FG	FH																1				
3.3 µF	335	J	K	M	FF	FF	FF	FM	FM																1				
3.9 µF	395	J	K	M	FG	FG	FG	FG	FK																				
4.7 μF	475	J	K	M	FC	FC	FC	FG	FS							GK	GK								JF	JF			
5.6 µF	565	J	K	M	FF	FF	FF	FH																					
6.8 µF	685	J	K	M	FG	FG	FG	FM																					
8.2 µF	825	J	K	M	FH	FH	FH	FK																					
10 µF	106	J	K	M	FH	FH	FH	FS								GK									JF	JO			
12 µF	126	J	K	M																									
15 µF	156	J	K	M																					JO				
18 µF	186	J	K	M																									
22 µF	226	J	K	M	FS	FS			-																JO				
	•		ed Vol (VDC)		6.3	9	16	25	50	100	200	250	50	100	200	25	50	100	200	250	50	10	200	250	25	50	100	200	250
Capacitance	Cap Code	Volt	tage C	Code	9	8	4	3	5	1	2	A	5	1	2	3	5	1	2	A	5	1	2	A	3	5	1	2	Α
	0000		se S Serie					C12	10C				с	1808	SC		С	1812	2C			C18	25C			С	2220	С	

*Capacitance range includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82 and 91) **Capacitance range includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68 and 82)



Table 2 – Chip Thickness/Tape & Reel Packaging Quantities

Thickness	Case	Thickness ±	Paper Q	luantity ¹	Plastic (Quantity	
Code	Size ¹	Range (mm)	7" Reel	13" Reel	7" Reel	13" Reel	
BB CF DN DP	0402 0603 0805 0805	$\begin{array}{c} 0.50 \pm 0.05 \\ 0.80 \pm 0.07 \\ 0.78 \pm 0.10 \\ 0.90 \pm 0.10 \end{array}$	10,000 4,000 4,000 4,000	50,000 15,000 15,000 15,000 15,000	0 0 0 0	0 0 0 0	
DE	0805	1.00 ± 0.10	0	0	2,500	10,000	
DG DH EB EC EN	0805 0805 1206 1206 1206	$\begin{array}{c} 1.25 \pm 0.15 \\ 1.25 \pm 0.20 \\ 0.78 \pm 0.10 \\ 0.90 \pm 0.10 \\ 0.95 \pm 0.10 \end{array}$	0 0 4,000 0 0	0 0 10,000 0 0	2,500 2,500 4,000 4,000 4,000	10,000 10,000 10,000 10,000 10,000	
ED EE EF EM EG	1206 1206 1206 1206 1206	$\begin{array}{c} 1.00 \pm 0.10 \\ 1.10 \pm 0.10 \\ 1.20 \pm 0.15 \\ 1.25 \pm 0.15 \\ 1.60 \pm 0.15 \end{array}$	0 0 0 0	0 0 0 0 0	2,500 2,500 2,500 2,500 2,500 2,000	10,000 10,000 10,000 10,000 8,000	
EH FB FC FD FE	1206 1210 1210 1210 1210 1210	$\begin{array}{c} 1.60 \pm 0.20 \\ 0.78 \pm 0.10 \\ 0.90 \pm 0.10 \\ 0.95 \pm 0.10 \\ 1.00 \pm 0.10 \end{array}$	0 0 0 0 0	0 0 0 0 0	2,000 4,000 4,000 4,000 2,500	8,000 10,000 10,000 10,000 10,000 10,000	
FF FG FL FH FM	1210 1210 1210 1210 1210 1210	$\begin{array}{c} 1.10 \pm 0.10 \\ 1.25 \pm 0.15 \\ 1.40 \pm 0.15 \\ 1.55 \pm 0.15 \\ 1.70 \pm 0.20 \end{array}$	0 0 0 0	0 0 0 0 0	2,500 2,500 2,000 2,000 2,000 2,000	10,000 10,000 8,000 8,000 8,000 8,000	
FJ FK FS NA NC	1210 1210 1210 1706 1706	$\begin{array}{c} 1.85 \pm 0.20 \\ 2.10 \pm 0.20 \\ 2.50 \pm 0.30 \\ 0.90 \pm 0.10 \\ 1.00 \pm 0.15 \end{array}$	0 0 0 0 0	0 0 0 0 0	2,000 2,000 1,000 4,000 4,000	8,000 8,000 4,000 10,000 10,000	
LD LF GB GC GD	1808 1808 1812 1812 1812 1812	$\begin{array}{c} 0.90 \pm 0.10 \\ 1.00 \pm 0.15 \\ 1.00 \pm 0.10 \\ 1.10 \pm 0.10 \\ 1.25 \pm 0.15 \end{array}$	0 0 0 0	0 0 0 0 0	2,500 2,500 1,000 1,000 1,000	10,000 10,000 4,000 4,000 4,000	
GE GH GG GK GJ	1812 1812 1812 1812 1812 1812	1.30 ± 0.10 1.40 ± 0.15 1.55 ± 0.10 1.60 ± 0.20 1.70 ± 0.15	0 0 0 0	0 0 0 0 0	1,000 1,000 1,000 1,000 1,000	4,000 4,000 4,000 4,000 4,000	
GO HB HD HF JB	1812 1825 1825 1825 2220	$2.50 \pm 0.20 \\ 1.10 \pm 0.15 \\ 1.30 \pm 0.15 \\ 1.50 \pm 0.15 \\ 1.00 \pm 0.15 \\ $	0 0 0 0	0 0 0 0 0	500 1,000 1,000 1,000 1,000	2,000 4,000 4,000 4,000 4,000 4,000	
JC JD JE JF JO	2220 2220 2220 2220 2220 2220 2220	1.00 ± 0.13 1.10 ± 0.15 1.30 ± 0.15 1.40 ± 0.15 1.50 ± 0.15 2.40 ± 0.15	0 0 0 0 0	0 0 0 0 0	1,000 1,000 1,000 1,000 500	4,000 4,000 4,000 4,000 4,000 2,000	
Thickness	Case	Thickness ±	7" Reel	13" Reel	7" Reel	13" Reel	
Code	Size ¹	Range (mm)	Paper Q	luantity ¹			

Package quantity based on finished chip thickness specifications.

¹ If ordering using the 2 mm Tape and Reel pitch option, the packaging quantity outlined in the table above will be doubled. This option is limited to EIA 0603 (1608 metric) case size devices. For more information regarding 2 mm pitch option see "Tape & Reel Packaging Information".



Table 3 – Chip Capacitor Land Pattern Design Recommendations per IPC–7351


EIA Size Code	Metric Size Code	Density Level A: Maximum (Most) Land Protrusion (mm)				Density Level B: Median (Nominal) Land Protrusion (mm)					Density Level C: Minimum (Least) Land Protrusion (mm)					
ooue	oode	С	Y	X	V1	V2	С	Y	X	V1	V2	С	Y	Х	V1	V2
0402	1005	0.50	0.72	0.72	2.20	1.20	0.45	0.62	0.62	1.90	1.00	0.40	0.52	0.52	1.60	0.80
0603	1608	0.90	1.15	1.10	4.00	2.10	0.80	0.95	1.00	3.10	1.50	0.60	0.75	0.90	2.40	1.20
0805	2012	1.00	1.35	1.55	4.40	2.60	0.90	1.15	1.45	3.50	2.00	0.75	0.95	1.35	2.80	1.70
1206	3216	1.60	1.35	1.90	5.60	2.90	1.50	1.15	1.80	4.70	2.30	1.40	0.95	1.70	4.00	2.00
1210	3225	1.60	1.35	2.80	5.65	3.80	1.50	1.15	2.70	4.70	3.20	1.40	0.95	2.60	4.00	2.90
1210 ¹	3225	1.50	1.60	2.90	5.60	3.90	1.40	1.40	2.80	4.70	3.30	1.30	1.20	2.70	4.00	3.00
1812	4532	2.15	1.60	3.60	6.90	4.60	2.05	1.40	3.50	6.00	4.00	1.95	1.20	3.40	5.30	3.70
2220	5650	2.75	1.70	5.50	8.20	6.50	2.65	1.50	5.40	7.30	5.90	2.55	1.30	5.30	6.60	5.60

¹ Only for capacitance values \geq 22 μ F

Density Level A: For low-density product applications. Recommended for wave solder applications and provides a wider process window for reflow solder processes. KEMET only recommends wave soldering of EIA 0603, 0805, and 1206 case sizes.

Density Level B: For products with a moderate level of component density. Provides a robust solder attachment condition for reflow solder processes. **Density Level C:** For high component density product applications. Before adapting the minimum land pattern variations the user should perform qualification testing based on the conditions outlined in IPC Standard 7351 (IPC–7351).

Image below based on Density Level B for an EIA 1210 case size.





Soldering Process


Recommended Soldering Technique:

- Solder wave or solder reflow for EIA case sizes 0603, 0805 and 1206
- All other EIA case sizes are limited to solder reflow only

Recommended Reflow Soldering Profile:

KEMET's families of surface mount multilayer ceramic capacitors (SMD MLCCs) are compatible with wave (single or dual), convection, IR or vapor phase reflow techniques. Preheating of these components is recommended to avoid extreme thermal stress. KEMET's recommended profile conditions for convection and IR reflow reflect the profile conditions of the IPC/J-STD-020 standard for moisture sensitivity testing. These devices can safely withstand a maximum of three reflow passes at these conditions.

Profile Feature	Terminati	on Finish
FIOINE Feature	SnPb	100% Matte Sn
Preheat/Soak		
Temperature Minimum (T _{Smin})	100°C	150°C
Temperature Maximum (T _{Smax})	150°C	200°C
Time (t _s) from T_{Smin} to T_{Smax}	60 – 120 seconds	60 – 120 seconds
Ramp-Up Rate $(T_L \text{ to } T_P)$	3°C/second maximum	3°C/second maximum
Liquidous Temperature (T_L)	183°C	217°C
Time Above Liquidous (t_L)	60 – 150 seconds	60 – 150 seconds
Peak Temperature (T _P)	235°C	260°C
Time Within 5°C of Maximum Peak Temperature (t _P)	20 seconds maximum	30 seconds maximum
Ramp-Down Rate $(T_P \text{ to } T_L)$	6°C/second maximum	6°C/second maximum
Time 25°C to Peak Temperature	6 minutes maximum	8 minutes maximum




Note 1: All temperatures refer to the center of the package, measured on the capacitor body surface that is facing up during assembly reflow.

Storage and Handling

Ceramic chip capacitors should be stored in normal working environments. While the chips themselves are quite robust in other environments, solderability will be degraded by exposure to high temperatures, high humidity, corrosive atmospheres, and long term storage. In addition, packaging materials will be degraded by high temperature– reels may soften or warp and tape peel force may increase. KEMET recommends that maximum storage temperature not exceed 40°C and maximum storage humidity not exceed 70% relative humidity. Temperature fluctuations should be minimized to avoid condensation on the parts and atmospheres should be free of chlorine and sulfur bearing compounds. For optimized solderability chip stock should be used promptly, preferably within 1.5 years of receipt.



Construction (Typical)





14

Capacitor Marking (Optional):

These surface mount multilayer ceramic capacitors are normally supplied unmarked. If required, they can be marked as an extra cost option. Marking is available on most KEMET devices but must be requested using the correct ordering code identifier(s). If this option is requested, two sides of the ceramic body will be laser marked with a "K" to identify KEMET, followed by two characters (per EIA–198 - see table below) to identify the capacitance value. EIA 0603 case size devices are limited to the "K" character only.

Laser marking option is <u>not</u> available on:

- C0G, Ultra Stable X8R and Y5V dielectric devices
- EIA 0402 case size devices
- EIA 0603 case size devices with Flexible Termination option.
- · KPS Commercial and Automotive Grade stacked devices.
- · X7R dielectric products in capacitance values outlined below

EIA Case Size	Metric Size Code	Capacitance
0603	1608	≤ 170 pF
0805	2012	≤ 150 pF
1206	3216	≤ 910 pF
1210	3225	≤ 2,000 pF
1808	4520	≤ 3,900 pF
1812	4532	≤ 6,700 pF
1825	4564	≤ 0.018 µF
2220	5650	≤ 0.027 µF
2225	5664	≤ 0.033 µF

Marking appears in legible contrast. Illustrated below is an example of an MLCC with laser marking of "KA8", which designates a KEMET device with rated capacitance of 100 μ F. Orientation of marking is vendor optional.



Capacitor Marking (Optional) cont'd

	Capacitance (pF) For Various Alpha/Numeral Identifiers										
						Numera	al				
Alpha	9	0	1	2	3	4	5	6	7	8	
Character		1		1	Capa	acitance	e (pF)				
A	0.1	10	10	100	1,000	10,000	100,000	1,000,000	10,000,000	100,000,000	
В	0.11	1.1	11	110	1,100	11,000	110,000	1,100,000	11,000,000	110,000,000	
С	0.12	12	12	120	1,200	12,000	120,000	1,200,000	12,000,000	120,000,000	
D	0.13	13	13	130	1,300	13,000	130,000	1,300,000	13,000,000	130,000,000	
E	0.15	15	15	150	1,500	15,000	150,000	1,500,000	15,000,000	150,000,000	
F	0.16	16	16	160	1,600	16,000	160,000	1,600,000	16,000,000	160,000,000	
G	0.18	18	18	180	1,800	18,000	180,000	1,800,000	18,000,000	180,000,000	
Н	0.2	20	20	200	2,000	20,000	200,000	2,000,000	20,000,000	200,000,000	
J	0.22	22	22	220	2,200	22,000	220,000	2,200,000	22,000,000	220,000,000	
К	0.24	2.4	24	240	2,400	24,000	240,000	2,400,000	24,000,000	240,000,000	
L	0.27	2.7	27	270	2,700	27,000	270,000	2,700,000	27,000,000	270,000,000	
М	0.3	30	30	300	3,000	30,000	300,000	3,000,000	30,000,000	300,000,000	
N	0.33	33	33	330	3,300	33,000	330,000	3,300,000	33,000,000	330,000,000	
Р	0.36	36	36	360	3,600	36,000	360,000	3,600,000	36,000,000	360,000,000	
Q	0.39	39	39	390	3,900	39,000	390,000	3,900,000	39,000,000	390,000,000	
R	0.43	4 3	43	430	4,300	43,000	430,000	4,300,000	43,000,000	430,000,000	
S	0.47	4.7	47	470	4,700	47,000	470,000	4,700,000	47,000,000	470,000,000	
Т	0.51	5.1	51	510	5,100	51,000	510,000	5,100,000	51,000,000	510,000,000	
U	0.56	56	56	560	5,600	56,000	560,000	5,600,000	56,000,000	560,000,000	
V	0.62	62	62	620	6,200	62,000	620,000	6,200,000	62,000,000	620,000,000	
W	0.68	68	68	680	6,800	68,000	680,000	6,800,000	68,000,000	680,000,000	
Х	0.75	75	75	750	7,500	75,000	750,000	7,500,000	75,000,000	750,000,000	
Y	0.82	82	82	820	8,200	82,000	820,000	8,200,000	82,000,000	820,000,000	
Z	0.91	9.1	91	910	9,100	91,000	910,000	9,100,000	91,000,000	910,000,000	
а	0.25	2 5	25	250	2,500	25,000	250,000	2,500,000	25,000,000	250,000,000	
b	0.35	35	35	350	3,500	35,000	350,000	3,500,000	35,000,000	350,000,000	
d	0.4	40	40	400	4,000	40,000	400,000	4,000,000	40,000,000	400,000,000	
e	0.45	4 5	45	450	4,500	45,000	450,000	4,500,000	45,000,000	450,000,000	
f	0.5	50	50	500	5,000	50,000	500,000	5,000,000	50,000,000	500,000,000	
m	0.6	60	60	600	6,000	60,000	600,000	6,000,000	60,000,000	600,000,000	
n	0.7	70	70	700	7,000	70,000	700,000	7,000,000	70,000,000	700,000,000	
t	0.8	80	80	800	8,000	80,000	800,000	8,000,000	80,000,000	800,000,000	
y	0.9	90	90	900	9,000	90,000	900,000	9,000,000	90,000,000	900,000,000	

Tape & Reel Packaging Information

KEMET offers multilayer ceramic chip capacitors packaged in 8, 12 and 16 mm tape on 7" and 13" reels in accordance with EIA Standard 481. This packaging system is compatible with all tape-fed automatic pick and place systems. See Table 2 for details on reeling quantities for commercial chips.




Table 5 – Carrier Tape Configuration, Embossed Plastic & Punched Paper (mm)

	Таре	Embosse	ed Plastic	Punche	d Paper	
EIA Case Size	Size	7" Reel	13" Reel	7" Reel	13" Reel	
	(W)*	Pitch (P ₁)*		Pitch (P ₁)*		
01005 – 0402	8			2	2	
0603	8			2/4	2/4 🖊	
0805	8	4	4	4	4	
1206 – 1210	8	4	4	4	4	
1805 – 1808	12	4	4			
≥ 1812	12	8	8			
KPS 1210	12	8	8			
KPS 1812 & 2220	16	12	12			
Array 0508 & 0612	8	4	4			

*Refer to Figures 1 & 2 for W and P₁ carrier tape reference locations. *Refer to Tables 6 & 7 for tolerance specifications.

New 2 mm Pitch Reel Options*

Packaging Ordering Code (C-Spec)	Packaging Type/Options
C-3190	Automotive grade 7" reel unmarked
C-3191	Automotive grade 13" reel unmarked
C-7081	Commercial grade 7" reel unmarked
C-7082	Commercial grade 13" reel unmarked

* 2 mm pitch reel only available for 0603 EIA case size.

2 mm pitch reel for 0805 EIA case size under development.

Benefits of Changing from 4 mm to 2 mm Pitching Spacing

- Lower placement costs
- Double the parts on each reel results in fewer reel changes and increased efficiency
- Fewer reels result in lower packaging, shipping and storage costs, reducing waste

Figure 1 – Embossed (Plastic) Carrier Tape Dimensions




Table 6 – Embossed (Plastic) Carrier Tape Dimensions

Metric will govern

			Constant Dim	ensions — Mi	llimeters (Incl	nes)			
Tape Size	D ₀	D ₁ Minimum Note 1	E ₁	P ₀	P ₂	R Reference Note 2	S ₁ Minimum Note 3	T Maximum	T₁ Maximum
8 mm		1.0 (0.039)				25.0 (0.984)			
12 mm	1.5 +0.10/-0.0 (0.059 +0.004/-0.0)	1.5	1.75 ±0.10 (0.069 ±0.004)	4.0 ±0.10 (0.157 ±0.004)	2.0 ±0.05 (0.079 ±0.002)	30	0.600 (0.024)	0.600 (0.024)	0.100 (0.004)
16 mm		(0.059)				(1.181)			
			Variable Dime	ensions — Mil	limeters (Inch	es)			
Tape Size	Pitch	B ₁ Maximum Note 4	E ₂ Minimum	F	P ₁	T ₂ Maximum	W Maximum	A ₀ ,B ₀	& K ₀
8 mm	Single (4 mm)	4.35 (0.171)	6.25 (0.246)	3.5 ±0.05 (0.138 ±0.002)	4.0 ±0.10 (0.157 ±0.004)	2.5 (0.098)	8.3 (0.327)		
12 mm	Single (4 mm) & Double (8 mm)	8.2 (0.323)	10.25 (0.404)	5.5 ±0.05 (0.217 ±0.002)	8.0 ±0.10 (0.315 ±0.004)	4.6 (0.181)	12.3 (0.484)	Not	ie 5
16 mm	Triple (12 mm)	12.1 (0.476)	14.25 (0.561)	7.5 ±0.05 (0.138 ±0.002)	12.0 ±0.10 (0.157 ±0.004)	4.6 (0.181)	16.3 (0.642)		

1. The embossment hole location shall be measured from the sprocket hole controlling the location of the embossment. Dimensions of embossment location and hole location shall be applied independent of each other.

2. The tape with or without components shall pass around R without damage (see Figure 6).

3. If S₁ < 1.0 mm, there may not be enough area for cover tape to be properly applied (see EIA Standard 481 paragraph 4.3 section b).

4. B, dimension is a reference dimension for tape feeder clearance only.

5. The cavity defined by A_{α} , B_{α} and K_{α} shall surround the component with sufficient clearance that:

(a) the component does not protrude above the top surface of the carrier tape.

(b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been removed.

(c) rotation of the component is limited to 20° maximum for 8 and 12 mm tapes and 10° maximum for 16 mm tapes (see Figure 3).

(d) lateral movement of the component is restricted to 0.5 mm maximum for 8 and 12 mm wide tape and to 1.0 mm maximum for 16 mm tape (see Figure 4).

(e) for KPS Series product, A_0 and B_0 are measured on a plane 0.3 mm above the bottom of the pocket.

(f) see Addendum in EIA Standard 481 for standards relating to more precise taping requirements.



Figure 2 – Punched (Paper) Carrier Tape Dimensions




Table 7 – Punched (Paper) Carrier Tape Dimensions

Metric will govern

	Constant Dimensions — Millimeters (Inches)										
Tape Size	D ₀	E ₁	P ₀	P ₂	T ₁ Maximum	G Minimum	R Reference Note 2				
8 mm	1.5 +0.10 -0.0 (0.059 +0.004 -0.0)	1.75 ±0.10 (0.069 ±0.004)	4.0 ±0.10 (0.157 ±0.004)	2.0 ±0.05 (0.079 ±0.002)	0.10 (0.004) Maximum	0.75 (0.030)	25 (0.984)				
	Variable Dimensions — Millimeters (Inches)										
Tape Size	Pitch	E2 Minimum	F	P ₁	T Maximum	W Maximum	A_0B_0				
8 mm	Half (2 mm)	6.25	3.5 ±0.05	2.0 ±0.05 (0.079 ±0.002)	1.1	8.3 (0.327)	Note 1				
8 mm	Single (4 mm)	(0.246)	(0.138 ±0.002)	4.0 ±0.10 (0.157 ±0.004)	(0.098)	8.3 (0.327)	NOLE I				

1. The cavity defined by A_{α} , B_{α} and T shall surround the component with sufficient clearance that:

a) the component does not protrude beyond either surface of the carrier tape.

b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been removed.

c) rotation of the component is limited to 20° maximum (see Figure 3).

d) lateral movement of the component is restricted to 0.5 mm maximum (see Figure 4).

e) see Addendum in EIA Standard 481 for standards relating to more precise taping requirements.

2. The tape with or without components shall pass around R without damage (see Figure 6).



Packaging Information Performance Notes

- 1. Cover Tape Break Force: 1.0 Kg minimum.
- 2. Cover Tape Peel Strength: The total peel strength of the cover tape from the carrier tape shall be:

Tape Width	Peel Strength
8 mm	0.1 to 1.0 Newton (10 to 100 gf)
12 and 16 mm	0.1 to 1.3 Newton (10 to 130 gf)

The direction of the pull shall be opposite the direction of the carrier tape travel. The pull angle of the carrier tape shall be 165° to 180° from the plane of the carrier tape. During peeling, the carrier and/or cover tape shall be pulled at a velocity of 300 ± 10 mm/minute. **3. Labeling:** Bar code labeling (standard or custom) shall be on the side of the reel opposite the sprocket holes. *Refer to EIA Standards* 556 *and* 624.

Figure 3 – Maximum Component Rotation




Figure 4 – Maximum Lateral Movement




Figure 5 – Bending Radius







Figure 6 – Reel Dimensions



Note: Drive spokes optional; if used, dimensions B and D shall apply.

Table 8 – Reel Dimensions

Metric will govern

	Constan	t Dimensions — Millimete	rs (Inches)							
Tape Size	A	B Minimum	С	D Minimum						
8 mm	178 ±0.20									
12 mm	(7.008 ±0.008) or	1.5 (0.059)	13.0 +0.5/-0.2 (0.521 +0.02/-0.008)	20.2 (0.795)						
16 mm	330 ±0.20 (13.000 ±0.008)		()	()						
	Variable Dimensions — Millimeters (Inches)									
Tape Size	N Minimum	W ₁	W ₂ Maximum	W ₃						
8 mm		8.4 +1.5/-0.0 (0.331 +0.059/-0.0)	14.4 (0.567)							
12 mm	50 (1.969)	12.4 +2.0/-0.0 (0.488 +0.078/-0.0)	18.4 (0.724)	Shall accommodate tape width without interference						
16 mm		16.4 +2.0/-0.0 (0.646 +0.078/-0.0)	22.4 (0.882)							



Figure 7 – Tape Leader & Trailer Dimensions





Figure 8 – Maximum Camber



Surface Mount Multilayer Ceramic Chip Capacitors (SMD MLCCs) – X7R Dielectric, 6.3 – 250 VDC (Automotive Grade)



KEMET Corporation World Headquarters

2835 KEMET Way Simpsonville, SC 29681

Mailing Address: P.O. Box 5928 Greenville, SC 29606

www.kemet.com Tel: 864-963-6300 Fax: 864-963-6521

Corporate Offices Fort Lauderdale, FL Tel: 954-766-2800

North America

Northeast Wilmington, MA Tel: 978-658-1663

Southeast Lake Mary, FL Tel: 407-855-8886

Central Novi, MI Tel: 248-994-1030

Irving, TX Tel: 972-915-6041

West Milpitas, CA Tel: 408-433-9950

Mexico Guadalajara, Jalisco Tel: 52-33-3123-2141

Europe

Southern Europe Sasso Marconi, Italy Tel: 39-051-939111

Skopje, Macedonia Tel: 389-2-55-14-623

Central Europe Landsberg, Germany Tel: 49-8191-3350800

Kamen, Germany Tel: 49-2307-438110

Northern Europe Wyboston, United Kingdom Tel: 44-1480-273082

Espoo, Finland Tel: 358-9-5406-5000

Asia

Northeast Asia Hong Kong Tel: 852-2305-1168

Shenzhen, China Tel: 86-755-2518-1306

Beijing, China Tel: 86-10-5877-1075

Shanghai, China Tel: 86-21-6447-0707

Seoul, South Korea Tel: 82-2-6294-0550

Taipei, Taiwan Tel: 886-2-27528585

Southeast Asia Singapore Tel: 65-6701-8033

Penang, Malaysia Tel: 60-4-6430200

Bangalore, India Tel: 91-806-53-76817

Note: KEMET reserves the right to modify minor details of internal and external construction at any time in the interest of product improvement. KEMET does not assume any responsibility for infringement that might result from the use of KEMET Capacitors in potential circuit designs. KEMET is a registered trademark of KEMET Electronics Corporation.

Disclaimer

All product specifications, statements, information and data (collectively, the "Information") in this datasheet are subject to change. The customer is responsible for checking and verifying the extent to which the Information contained in this publication is applicable to an order at the time the order is placed.

All Information given herein is believed to be accurate and reliable, but it is presented without guarantee, warranty, or responsibility of any kind, expressed or implied.

Statements of suitability for certain applications are based on KEMET Electronics Corporation's ("KEMET") knowledge of typical operating conditions for such applications, but are not intended to constitute – and KEMET specifically disclaims – any warranty concerning suitability for a specific customer application or use. The Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by KEMET with reference to the use of KEMET's products is given gratis, and KEMET assumes no obligation or liability for the advice given or results obtained.

Although KEMET designs and manufactures its products to the most stringent quality and safety standards, given the current state of the art, isolated component failures may still occur. Accordingly, customer applications which require a high degree of reliability or safety should employ suitable designs or other safeguards (such as installation of protective circuitry or redundancies) in order to ensure that the failure of an electrical component does not result in a risk of personal injury or property damage.

Although all product-related warnings, cautions and notes must be observed, the customer should not assume that all safety measures are indicted or that other measures may not be required.