

SPECIFICATION

- Supplier : Samsung electro-mechanics
- Product : Multi-layer Ceramic Capacitor

- Samsung P/N : **CL03C120JA3GNNC**
- Description : **CAP, 12pF, 25V, ±5%, C0G, 0201**

A. Samsung Part Number

CL 03 C 120 J A 3 G N N C
 ① ② ③ ④ ⑤ ⑥ ⑦ ⑧ ⑨ ⑩ ⑪

| | | | |
|-------------------------|---------------------------------------|-------------------|------------------------------------|
| ① Series | Samsung Multi-layer Ceramic Capacitor | | |
| ② Size | 0201 (inch code) | L: 0.6 ± 0.03 mm | W: 0.3 ± 0.03 mm |
| ③ Dielectric | C0G | ⑧ Inner electrode | Cu |
| ④ Capacitance | 12 pF | Termination | Cu |
| ⑤ Capacitance tolerance | ±5 % | Plating | Sn 100% (Pb Free) |
| ⑥ Rated Voltage | 25 V | ⑨ Product | Normal |
| ⑦ Thickness | 0.3 ± 0.03 mm | ⑩ Special | Reserved for future use |
| | | ⑪ Packaging | Cardboard Type, 7" reel (10,000ea) |

B. Samsung Reliability Test and Judgement condition

| | Performance | Test condition |
|----------------------------------|--|--|
| Capacitance | Within specified tolerance | 1MHz±10% 0.5~5Vrms |
| Q | 640 min | |
| Insulation Resistance | More than 500Mohm·μF | Rated Voltage 60~120 sec. |
| Appearance | No abnormal exterior appearance | Visual inspection |
| Withstanding Voltage | No dielectric breakdown or mechanical breakdown | 300% of the rated voltage |
| Temperature Characteristics | C0G (From -55℃ to 125℃, Capacitance change should be within ±30PPM/℃) | |
| Adhesive Strength of Termination | No peeling shall be occur on the terminal electrode | 200g·F, for 10±1 sec. |
| Bending Strength | Capacitance change : within ±5% | Bending to the limit (1mm) with 1.0mm/sec. |
| Solderability | More than 75% of terminal surface is to be soldered newly | SnAg3.0Cu0.5 solder 245±5℃, 3±0.3sec. (preheating : 80~120℃ for 10~30sec.) |
| Resistance to Soldering heat | Capacitance change : within ±2.5% Tan δ, IR : initial spec. | Solder pot : 270±5℃, 10±1sec. |

| | Performance | Test condition |
|------------------------------------|--|--|
| Vibration Test | Capacitance change : within $\pm 2.5\%$ Tan δ , IR : initial spec. | Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours \times 3 direction (x, y, z) |
| Moisture Resistance | Capacitance change : within $\pm 7.5\%$ Q : 140 min IR : More than $25M\Omega \cdot \mu F$ | With rated voltage $40 \pm 2^\circ C$, 90~95%RH, 500 +12/-0 hour |
| High Temperature Resistance | Capacitance change : within $\pm 3\%$ Q : 305 min IR : More than $50M\Omega \cdot \mu F$ | With 200% of the rated voltage Max. operating temperature 1000+48/-0 hour |
| Temperature Cycling | Capacitance change : within $\pm 2.5\%$ Tan δ , IR : initial spec. | 1 cycle condition Min. operating temperature $\rightarrow 25^\circ C$ \rightarrow Max. operating temperature $\rightarrow 25^\circ C$ 5 cycles test |

C. Recommended Soldering method :

Reflow (Reflow Peak Temperature : $260 \pm 0/-5^\circ C$, 10sec. Max)

* For the more detail Specification, Please refer to the Samsung MLCC catalogue.